




PIPING SYSTEM PTE LTD  
PROFESSIONAL SUPPLIER OF PIPELINE MATERIALS AND EQUIPMENT

DRAWING NO.: ELBOW-DRAWING-AND-DATA-2026-02-25-14-16  
DRAWING DATE: 25-Feb-2026

## ELBOW DRAWING AND DIMENSIONS DATA

|         |          |              |                                                                                                                            |
|---------|----------|--------------|----------------------------------------------------------------------------------------------------------------------------|
| OR No.: | OR999999 | DESCRIPTION: | ELBOW-¾INCHES-90DEG-BEVELLED ENDS-SEAMLESS-SCHSTD(2.87MM)-CARBON STEEL-LONG RADIUS-GR WPB-ASTM A234-ASME B16.9-NACE MR0175 |
| ITEM:   | 68       |              |                                                                                                                            |



ANSI ASME B16.9 / MSS SP-75 (in mm)

| ITEM | NAME  | TYPE   | DEGREE | MATERIAL STANDARD            | DN | OD INCH(ES) | ODMM | UNIT<br>Volume (m³) | DIMENSIONS(MM) |         |      |
|------|-------|--------|--------|------------------------------|----|-------------|------|---------------------|----------------|---------|------|
|      |       |        |        |                              |    |             |      |                     | L=A+½OD        | W=A+½OD | H=OD |
| 68   | ELBOW | R=1.5D | 90     | ASTM<br>A234/A234M<br>GR WPB | 20 | ¾           | 26.7 | 0.00007068          | 51.45          | 51.45   | 26.7 |

MATERIAL STANDARD: ASTM A234/A234M GR WPB Chemical element composition content (%)

| COMPONENT | C   | Si  | Mn   | P    | S     | Cr  | Ni  | Cu  | Mo   | V    |
|-----------|-----|-----|------|------|-------|-----|-----|-----|------|------|
| Max       | —   | —   | 0.29 | —    | —     | —   | —   | —   | —    | —    |
| Min       | 0.3 | 0.1 | 1.06 | 0.05 | 0.058 | 0.4 | 0.4 | 0.4 | 0.15 | 0.08 |

ASTM A234/A234M GR WPB Mechanical Properties

| Condition     | TENSILE STRENGTH<br>$\sigma_b$<br>Mpa | YIELD POINT<br>$\sigma_s$<br>Mpa | ELONGATION OR ELONGATION AT BREAK<br>$\delta$<br>%                                                                                  |
|---------------|---------------------------------------|----------------------------------|-------------------------------------------------------------------------------------------------------------------------------------|
| PIPE FITTINGS | ≥415                                  | ≥240                             | Standard round specimen, or small specimen, or strip specimen<br>long. : tr. :<br>L0=4D: ≥22* L0=4D: ≥14*<br>L0=50: ≥30© L0=50: ≥20 |



PIPING SYSTEM PTE LTD  
[HTTPS://PIPING.COM.CN](https://piping.com.cn)  
PROFESSIONAL SUPPLIER OF PIPELINE MATERIALS AND EQUIPMENT  
STANDING IN SINGAPORE, SERVING THE WORLD

DRAWING

HuBiao

AUDIT

王建

APPROVAL

王